Surface Combustion

Atmospheres For Heat Treating Equipment

SECOND EDITION



Atmospheres for Heat Treating Equipment

This publication is intended to provide an overview and documented general information in regard to atmospheres used in heat treating furnaces. It is distributed with the understanding that numerous items can effect the analysis of atmospheres used and the resulting metallurgical properties of materials being heat treated. Surface Combustion takes no responsibilities for the user's thermal process, the resulting conditions of materials heat treated, or the use of any of the materials or methods described in this booklet.

The reader is advised that this publication is released and distributed only with the express understandings that Surface Combustion, Inc., its officers, agents and employees i) makes no representation or warranty, express or implied, with respect to the accuracy, completeness or usefulness of the data or information presented herein and/or ii) assumes no liability for the use or misuse of any information, data, apparatus, processes or methods disclosed herein.

©2000 by Surface Combustion, Inc., Maumee, Ohio

Surface®, AX®, DX®, HNX®, HX®, NX®, and RX®
are registered trademarks of Surface Combustion, Inc.

ASRX™, Char-Mo™, and SRX™ are trademarks
of Surface Combustion, Inc.

Table of Contents

Generation, Application and Control of Furnace Atmospheres 2

Prepared Atmospheres Classifications 7
- Effect On Metals

Compositions and Characteristics For Various Classes Of Prepared Atmospheres 8

Endothermic Gas Generators Flow Diagrams 10

Endothermic Gas Generators Typical Gas Composition % By Volume 11
- Endothermic Gas Generators Applications

Exothermic Gas Generators Flow Diagrams 12

Exothermic Gas Generators Typical Gas Composition % By Volume 13
- Exothermic Gas Generators Applications

Ammonia Dissociator Flow Diagram 14
- Ammonia Dissociator Typical Composition % By Volume
- Ammonia Dissociator Applications

Heat Content Of Various Gases 15

Composition Of DX® Gas Made From Natural Gas For Various Air-Gas Ratios (Dry Basis) 18
- Approximate Required Volumes Of Atmosphere

Special Atmosphere Chart 19

Properties Of Common Gases and Vapors 20

Viscosity (μ) Of Gases 21
- Thermal Conductivity (k) Of Gases

Specific Heat (Cp) Of Gases 22
- Prandtl Number Of Gases

Equilibrium Curves For Furnace Gases On Iron, Carbon and Steels 23

Equilibrium Dew Point -vs- Percent Carbon In Austenite (RX® Gas) 24
- Carbon Potential Chart By CO_2 Equilibrium (RX® Gas)

Percent CO_2 -vs- Dew Point (RX® Gas) 25
- Carbon Potential Chart By CO_2 Equilibrium (RX® Gas) [Metric]

Percent Carbon Dioxide -vs- Percent Carbon In Austenite (RX® Gas) 26

Liquid Methanol Technical Data 27
- Thermal Cracking Of Methanol

Furnace Methane Levels At Various Temperatures Using Nitrogen Methanol Carrier And No Enriching Gas 28

Furnace Carbon Monoxide Levels At Various Temperatures Using Nitrogen Methanol Carrier ... 29

Protective Atmospheres - Applications, Types and Compositions 30

Brazing & Sintering Atmospheres - Applications, Types and Compositions 31

Carburizing Atmospheres - Applications, Types and Compositions 32

Effect Of Various Gas Constituents On Metals 33

Charcoal Based Atmosphere 34

Generation, Application and Control of Furnace Atmospheres - By William M. Dempster

The original source of furnace atmosphere for protection or change of heated metal surfaces was the combustion of a fuel, such as wood or coal, or oil. However, if combustion to provide heat was uncontrolled resulting in unreacted oxygen or in the case of hydrocarbons, undesirable water vapor, the resulting environment detrimentally affected the piece of metal being processed. Therefore, the first step was to provide an externally heated working chamber and introduce a prepared gas mixture to exclude air and accomplish the desired result.

There are various substances which can be combined with air to provide atmosphere gas suitable for a number of processes. The elements involved are: (1) a type of carbon bearing reactant; (2) a breakdown of this reactant with the absence of air; (3) various completenesses of reaction between this reactant and air; (4) a combination of hydrocarbon with steam; (5) removal of the products of a reaction by some means. The reactants most commonly used are: (1) carbon such as wood charcoal; (2) simple hydrocarbon gases such as methane, propane, and butane; (3) simple common hydrocarbon liquids such as methanol, ethanol, acetone, and complex hydrocarbons such as kerosene, No. 2 fuel oil, or toluene. The choice of reactants also is dependent on the end analysis desired, as some are suitable for one type of prepared gas, but not for another.

Certain forms of hydrocarbon are not suitable: (1) those containing sulphur (for example coal, coke and heavy petroleum compounds), which is destructive to most metals at high temperature and to most metallurgical processes; (2) complex hydrocarbons such as iso-propane and iso-butanes which will not react completely, or which will produce a solid carbon when they dissociate under heat; (3) reactant of analysis too inconsistent to accomplish certain metallurgical reactions.

Therefore, in choosing a reactant it should be the simplest and purest form of hydrocarbon. First, it is necessary to determine what metallurgical process is desired for the particular metal involved. These metals commonly are copper and brass, low carbon steel (up to .20% C), medium carbon steel (.20% C to .60% C), high carbon steel (.60% C and over), and stainless and special steels.

Hydrocarbon Reactions

The various gases produced in reactions of hydrocarbons with air ($0^2 + 4\ N_2$), and their reactions with common metals are shown in Table 1 (found at the end of this article). Nitrogen is considered inert to all metals, except for atomic nitrogen produced by the dissociation of ammonia which produces Fe_3N in nitriding applications.

The various atmosphere gas mixes available through the use of an external atmosphere generator, or internal furnace reaction device, and method of generation are as follows.

Charcoal Gas

Production is by controlled partial combustion of pure hardwood charcoal (minimum of impurities). Air under pressure flows up through a heated retort filled with the lump charcoal, after venting the undesirable gases from the green charcoal entering the retort from the top. The usable gas is drawn off the retort at its maximum temperature zone. The gas composition is 34.7% CO, 1.2% H_2, 64.1% N_2 and trace of CO_2 according to adjustment.

One kilogram (2.2 lb) of charcoal will provide approximately 5 cubic meters (176.5 cu.ft.) of gas. The gas will carburize and can be enriched for high carbon potentials in treating steel.

Lean Exothermic Gas

This gas is manufactured by the controlled combustion of hydrocarbons. It is prepared in a separate combustion chamber with proper ratio controls to ensure a constant analysis. The products of combustion are then cooled to 30°C (86°F) or less in a heat exchanger system in order to reduce the percentage of H_20.

An approximate analysis of this gas is CO_2 - 12. 7%, CO - 1 .0%, H_2 -1.0%, balance - N_2; dew point from 30°C to 5°C (86°F to 41°F). It is considered non-explosive, and would be suitable for bright annealing of copper. The gas can be manufactured from gaseous hydrocarbons, and from light hydrocarbon liquids. With the liquid fuels, the smallest sized generator would be approximately 30 cubic meters (1059 cu.ft.) per hour, and an additional step may be required to remove traces of SO_2 originating from the fuel.

The gas produces a blue finish on steel, or serves as an atmosphere for brazing.

Rich Exothermic Gas

This gas is produced in the same manner as the lean type, except that the combustion mixture is controlled to reduce the amount of O_2 in order to increase the amounts of CO and H_2. The average analysis of this gas is CO_2 - 6%, CO - 8%, H_2 - 8%, balance - N_2; dew point from 30°C to 5°C (86°F to 41°F). It can be manufactured from gaseous hydrocarbons, very light hydrocarbons such as CH_3 OH methanol and C_2H_5OH ethanol. The gas is considered explosive.

Applications of this gas include bright annealing low and medium carbon steels, brazing with bright finish or clean hardening low and medium carbon steels.

Nitrogen Gas

A nitrogen gas of 95% purity can be attained from a lean exothermic gas. The exo gas is purified by removal of SO_2 and then passed through a molecular sieve system to remove CO_2, part of the CO, and most remaining H_2O. The average analysis of this gas is CO_2 - 0.05%, CO - .25 to 1.0%, H_2 - .5 to 5.0%, N_2- balance; dew point - -30°C (-22°F).

This gas is used as an inert type to bright anneal steel and can be used for clean hardening operations.